



Product Information

Polyamide

| | | |
|-----------------------------------|--|-----------------------|
| Short Description | PA6 | |
| Designation | Polyamide | |
| Shape / colour | Cylindrical / cubic, /natural / red | |
| Application | deburring of thermoset parts (for example: switches or plugs in the electrical industries.) | |
| Blasting Systems | compressed air - and centrifugal wheel systems | |
| Indication / Chemical Composition | Polyamide | |
| Hardness (New Grain) | HRR 100 - 105 | |
| Hardness (Operating Mix) | Identical to New Grain | |
| Specific Density [kg/l] | 1,12 - 1,14 | |
| Bulk Density [kg/l] | 0,7 - 0,85 depends on particle size | |
| Specific Characteristics | melting point: > 215° C | |
| Storage | several years, considering dry storage | |
| Particle Size | cylindrical | cubic |
| | 0,50 x 0,50 mm | 0,75 x 0,75 x 0,75 mm |
| | 0,75 x 0,75 mm | 1,00 x 1,00 x 1,00 mm |
| | 1,00 x 1,00 mm | 1,27 x 1,27 x 1,27 mm |
| | 1,27 x 1,27 mm | 1,50 x 1,50 x 1,50 mm |
| | 1,50 x 1,50 mm | |