



## Product Information

### Steel cut wire FILGRA spherical

Short Description	StD-G	
Designation	Steel cut wire FILGRA (G2)	
Shape	Spherical	
Application	Cleaning, shot peening,	
Blasting Systems	Wheel blasting systems and compressed Air blasting systems	
Hardness (New Grain)	HV 500 = 1580/1770 N/mm <sup>2</sup> HV 640 = 1970/2160 N/mm <sup>2</sup>	
Specific Density [kg/l]	Approx. 7,60	
Bulk Density [kg/l]	Approx. 4,4	
Specific Characteristics	Shot peening with exactly defined grain sizes and specific selection of greater strengths	
Storage	Several years, considering dry storage	
Particle Size	0,90 mm	0,60 mm
	0,80 mm	0,50 mm
	0,70 mm	0,40 mm